Klüber Lubrication NA LP • 9010 CR 2120 Tyler, Texas 75707 • Phone 903.534.8021 • sales@klsummit.com

January 27, 2022

NOTE: The information in this publication is the result of careful testing in our laboratories, complemented by selected literature. It does not in any way constitute a guarantee, nor does it serve as a license to operate any patent. Due to widely varying conditions of product use, which are beyond our control, it is strongly recommended that the product be tested for suitability. Product typical properties in this publication are current.

SUMMIT

ALUMINUM COMPLEX THICKENED SEMI-SYNTHETIC

SumTech® FMG Series

SUMTECH® FMG grease is an aluminum complex thickened semi-synthetic lubricating grease created specifically for the food service, beverage, and packaging industries. The aluminum complex thickener system provides excellent water resistance and a broad operating temperature range. A combination of newly developed additives and dependable HX1 additives provide excellent anti-wear/extreme pressure properties, oxidation resistance, and corrosion prevention. Special additives are employed to keep the grease in place between wash-down cycles which improves equipment and lubricant life in wet conditions. SUMTECH® FMG grease is NSF Registered and meets USDA 1998 (H1) guidelines (lubricants with incidental food contact).

SUMTECH® FMG is ideal for lubrication of production equipment in beverage canning operations, bottling operations, meat and poultry processing, dairy operations, fruit and vegetable processing, bakeries, and pharmaceutical plants.

Physical Properties

| PRODUCTS | FMG-0 | FMG-1 | FMG-2 |
|--|--|--|--|
| NLGI Grade | 0 | 1 | 2 |
| Color | Off White to Yellov | Off White to Yellow | Off White to Yellow |
| Texture | Homogenous | Homogenous | Homogenous |
| Base Oil | Mineral Oil/PAO | Mineral Oil/PAO | Mineral Oil/PAO |
| Viscosity @ 40°C cSt Viscosity @ 100°C cSt Viscosity Index | Approx 150 cSt Approx 18 cSt 140 | Approx 150 cSt Approx 18 cSt 140 | Approx 150 cSt Approx 18 cSt 140 |
| Thickener Type | Aluminum Complex | Aluminum Complex | Aluminum Complex |
| Drop Point | 210°C (410°F) | 250°C (482°F) | 270°C (518°F) |
| Penetration Worked 60 dbl strokes | 355-385 | 310-340 | 265-295 |
| Oil Separation | Less than 10% | Less than 7% | Less than 3% |
| 4-Ball Wear ASTM D2266 | <0.55 mm | <0.55 mm | <0.55 mm |
| NSF Registered | H1 | H1 | H1 |
| Kosher Approved | Yes | Yes | Yes |
| Halal Approved | Yes | Yes | Yes |

Shelf Life: Product shelf life is 3 years from the date of manufacture, after which the product should be recertified prior to use.